

TEJIDOS REBÉS

BARCELONA
SINCE 1955



Artículo/Article		VIENA PRINTED TECNOSANI			
REUSABLE (>25 washes)		MADE IN SPAIN			
ANÁLISIS FÍSICO / PHYSICAL ANALYSIS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
Nº de Hilo/Thread Count	Urdimbre / Warp		30 1/C		
	Trama / Weft		30 1/C		
Densidad / Density	Urdimbre / Warp		68		
	Trama / Weft		68		
Ligamento / Weave		PLANA / PLAIN			
Comp. Urd./ Comp. Warp		100% COTTON		ISO 1833:2006	
Comp. Tr./ Comp. Weft		100% COTTON			
Total Comp.		100% COTTON		Simple: No tolerancia Compuesta: +/- 3%	
Ancho Final / Final Width		cm	150 - 155		+/- 2% ISO 3932:1976
Peso / Weight		gr/m ²	120 - 125		+/- 5% ISO 3801:1977
Resistencia Rotura/ Breakage	(Kgs.)	Urdimbre		pass	kgf EN-13795
		Trama		pass	kgf
Resistencia Abrasion		pass		EN-13795	
Resistencia Desgarro / Tear		Urdimbre/Warp (G)	N/A	Trama / Weft	N/A EN-13795
Encogimiento / Shrinkage		°C	60	% Urdimbre	+/- 3
				% Trama	+/- 3
SPECIAL MEDICAL TESTS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
Washing solidity 60°C		n/a (pending after first production)		0-5 UNE EN ISO-05	
Pilling		n/a (pending after first production)		0-5 UNE EN ISO 12945-2	
Traspirability		n/a (pending after first production)		AST1	
Aerosol Filtration Efficiency		n/a (pending after first production)		UNE EN14683	
Particle Filtration Efficiency		n/a (pending after first production)		UNE EN14683	
Particle Filtration		n/a (pending after first production)		UNE EN149	
Bacterial presence		DRY: PASS	WET: PASS	EN-13795	
ANÁLISIS QUÍMICO / CHEMICAL ANALYSIS					
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	
TEST					
pH		Conforme/According Oeko-Tex II		4,0 - 7,5 UNI EN ISO 3071/06	
Formaldehído		Conforme/According Oeko-Tex II		<16ppm	< 75ppm UNE EN ISO 14184-1:1999
Arlaminas		Conforme/According Oeko-Tex II		20 ppm UNE 2002/61/CE	
PROHIBIDOS / FORBIDDEN					
Metales Pesados		Conforme/According Oeko-Tex II		Niquel 0,5 Pg/cm ² - Cadmio 75 pm - Plomo 100 ppm	
AZO Colorants		Conforme/According Oeko-Tex II		No detectable	
Colorantes Alérgicos		Conforme/According Oeko-Tex II		No detectable (LMBG) (1/4/96)	
SÍMBOLOS DE LAVADO/ WASH CARE SYMBOLS					
Observaciones:					
TRAS 25 LAVADOS EL ACABADO EMPIEZA A PERDER PROPIEDADES - LAVAR CON DETERGENTE NEUTRO					
AFTER 25 WASHES THE FINISH BEGINS TO LOSE PROPERTIES - WASH WITH NEUTRAL DETERGENT					
NO USAR LEJIA / DO NOT USE BLEACHING					
PLANCHADO A 140° de 10-15 SEGUNDOS / IRON 140° FOR 10-15 SECONDS					
ORGANIC COTTON *GOTS bajo pedido / on request					